

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 8/32, C08L 23/02	A1	(11) International Publication Number: WO 96/27622 (43) International Publication Date: 12 September 1996 (12.09.96)
(21) International Application Number: PCT/CA96/00141 (22) International Filing Date: 6 March 1996 (06.03.96) (30) Priority Data: 08/400,160 7 March 1995 (07.03.95) US (71) Applicant: DUPONT CANADA INC. [CA/CA]; 7070 Mississauga Road, Mississauga, Ontario L5M 2H3 (CA). (72) Inventor: XIE, Haiqi; 901-828 Sutton Mills Court, Kingston, Ontario K7P 2S9 (CA). (74) Agent: GALLOWAY, Warren, J.; Sim & McBurney, Suite 701, 330 University Avenue, Toronto, Ontario M5G 1R7 (CA).	(81) Designated States: CA, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>	
(54) Title: NUCLEOPHILIC AMINE FUNCTIONALIZED POLYOLEFIN (57) Abstract <p>This invention relates to a method of producing nucleophilic amine functionalized polyolefins by reacting a polymer carrying an electrophilic functional group with a diamine having amino end-groups having different reactivities. The nucleophilic amine functionalized polyolefin has the composition: Polyolefin - X - R₁ - NHR₂ where X is selected from the group of imide, amide, sulphonamide or amine, R₁ is a bivalent organic radical, R₂ is H or an alkyl group. The nucleophilic amine functionalized polyolefin has uses as a compatibilizer, adhesive, dyeable material, and dyeability improver.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

TITLE**Nucleophilic Amine Functionalized Polyolefin****BACKGROUND OF INVENTION****Field of Invention**

5 This invention relates to nucleophilic amine functionalized polyolefins, a method of producing nucleophilic amine functionalized polyolefins by reacting a polymer carrying an electrophilic functional group with a diamine, and the use of same as compatibilizers to make blends of polyolefins which are otherwise incompatible.

10 Background Discussion and Related Art

 The blending of two or more polymers has attracted wide interest for a variety of reasons, including the development of new polymer blends and "alloys", new products, as well as the desire to recycle post-consumer plastic waste materials.

15 One of the technical difficulties with recycling of post-consumer plastic waste materials is the incompatibility of the different polymer materials found in plastic waste stream such as polypropylene, polyethylene, polystyrene, polyvinylchloride (PVC) and others. Generally speaking blends of incompatible or thermodynamically immiscible polymers produce blends
20 which exhibit poor mechanical properties and processing difficulties.

 Nucleophilic Amine Functionalized PolyOlefins (NAFPO's) are of interest for polymer blending and alloying, and hence the development of new polymeric materials. There are many commercial products of acid and anhydride functionalized polyolefin in the marketplace, but there are few
25 products which are effectively capable of reacting and/or coupling with same. Although nucleophilic amine functionalized materials can react and couple with acid and anhydride functionalized materials, NAFPO's are difficult to make because of the high reactivity of nucleophilic amines. For example, Exxon Corporation is developing a Ziegler-Natta copolymerization process
30 involving masking and demasking the amine functionality. Moreover, K.T. Chung of Penn State University utilizes a borane approach to make NAFPO's. Hydrogenation of acrylonitrile rubber can also yield nucleophilic amine containing nitrile rubber. However, these processes are relatively expensive and most of them are difficult to commercialize.

35 Other processes and compositions are disclosed in United States Patent No. 4,822,688 which relates to an adhesive composition consisting essentially of polypropylene modified by grafting with an acid

anhydride to further react with a compound bearing at least two groups capable of reacting with the anhydride.

Moreover, United States Patent No. 5,130,378 relates to copolymers prepared from olefinically unsaturated compounds having a molecular weight of 600 - 20,000 and containing 0.1% to 6.0% by weight of secondary amino groups.

Furthermore, Japanese Patent No. 93-274505/35 shows amino functional copolymers containing imide substituted by amino-alkyl.

It is an object of this invention to provide a new NAFPO composition and an improved method for producing NAFPO's. It is a further object of this invention to provide an improved compatibilizer to make blends of polyolefins with polar polymers.

SUMMARY OF INVENTION

The broadest aspect of this invention relates to a method of producing nucleophilic amine functionalized polyolefin by reacting: a polymer carrying an electrophilic functional group, with a diamine having amino groups of different reactivities or salts thereof. The process is preferably carried out under conditions to control cross-linking, particularly by operating in a manner to assure that the mole concentration of diamine remains greater than that of the electrophilic functional group throughout the reaction.

Another aspect of this invention relates to a nucleophilic amine functionalized polyolefin composition having the structure:

Polyolefin - X - R₁ - NHR₂

where X is selected from the group of imide, amide, sulphonamide or amine

R₁ is a bivalent organic radical

R₂ is H or an alkyl group.

Yet another aspect of this invention relates to a multi-phase thermoplastic composition consisting essentially of 0.2 - 99.8% by weight of Polyolefin A and 99.8% - 0.2% by weight of Polyolefin B where: said Polyolefin A and Polyolefin B are immiscible polymers selected from the group of homopolymer of ethylene, homopolymer of propylene, dipolymer of ethylene and propylene, terpolymers of ethylene, propylene and diene and, copolymers of two or more monomers selected from ethylene, propylene, C₄ -

C₁₈ alpha-olefin, and diene monomer; with Polyolefin A carrying an electrophilic functional group where the total amount of electrophilic functional Polyolefin A to Polyolefin A is between 0.1% to 100% by weight; Polyolefin B carrying a nucleophilic amine functional group where the total amount of nucleophilic amine functionalized Polyolefin B to Polyolefin B is between 0.1% to 100% by weight.

Yet a further aspect of this invention relates to a process for improving the blending of Polyolefin A and Polyolefin B where said Polyolefin A and Polyolefin B are immiscible polymers selected from the group of homopolymers of ethylene, homopolymers of propylene, terpolymers of ethylene, propylene and diene, copolymers of two or more monomers selected from ethylene, propylene, C₄ - C₁₈ alpha-olefin, and diene monomer by adding: Polyolefin A carrying an electrophilic functional group where the total amount of electrophilic functionalized Polyolefin A to Polyolefin A is between 0.1% to 100% by weight; Polyolefin B carrying a nucleophilic amine functionalized Polyolefin B where the total amount of nucleophilic amine functionalized Polyolefin B to Polyolefin B is between 0.1% to 100% by weight.

20 DETAILED DESCRIPTION OF INVENTION

This invention relates to a nucleophilic amine functionalized polyolefin composition and method of producing nucleophilic amine functionalized polyolefins.

The term "functional" or "functionalized" as used herein generally relates to the relatively high chemical reactivity of chemical groups or polymer materials.

The term "polyolefins" as used herein generally relates to homopolymer of ethylene, homopolymer of propylene, dipolymer of ethylene and propylene, terpolymers of ethylene, propylene and diene, and copolymers of two or more monomers selected from ethylene, propylene, C₄ - C₁₈ alpha-olefin, and diene monomer.

Examples of the C₄ - C₁₈ alpha-olefins include butene-1, hexene-1, and octene-1.

In particular, polyolefins of interest are polyethylene (PE), and polypropylene (PP).

The term "nucleophilic" as used herein generally relates to the capability of a base to form a covalent bond with carboxylic acid, anhydride, sulphonic acid, chlorinated hydrocarbon materials and epoxides.

More particularly, this invention relates to a method of producing nucleophilic amine functionalized polyolefins by reacting:

- (a) a polymer carrying an electrophilic functional group with
 - (b) a diamine or a salt of the diamine such as a carboxylate
- 5 thereof, the diamine preferably having the structure:



wherein R_1 is a bivalent organic radical (for example an alkyl group, preferably a C_2 to C_{18} alkyl group, with or without a tertiary amino group)

10 R_2 is a H or alkyl group, preferably a C_2 to C_{18} alkyl group.

Other diamines may be used provided that the end groups have different reactivities. Theoretically, aromatic diamines such as phenylene diamines should work but are not preferred since they are toxic, easily

15 oxidized and cause strong discoloration of products.

Examples of possibly useful diamines are as set forth in Table I.

Table I

Primary-Primary Diamines	
1,3-Pentanediamine (Dytek® EP)	$\text{H}_2\text{N}-\text{CH}_2-\text{CH}_2-\underset{\text{NH}_2}{\text{CH}}-\text{CH}_2-\text{CH}_3$
	$\text{H}_2\text{N}-\text{C}_n\text{H}_{2n}-\underset{\text{NH}_2}{\text{CH}}-\text{C}_p\text{H}_{2p+1}$
	$\text{H}_2\text{N}-\text{C}_n\text{H}_{2n}-\underset{\text{NH}_2}{\underset{\text{C}_m\text{H}_{2m+1}}{\text{CH}}}-\text{C}_p\text{H}_{2p+1}$
Primary-Secondary Diamines	
N-(2-Aminoethyl)piperazine (AEP)	$\begin{array}{c} \text{CH}_2-\text{CH}_2 \\ \quad \\ \text{H}_2\text{N}-\text{CH}_2-\text{CH}_2-\text{N} \quad \text{NH} \\ \quad \\ \text{CH}_2-\text{CH}_2 \end{array}$
2-(2-Aminoethyl)ethanolamine (AEEA)	$\text{H}_2\text{N}-\text{CH}_2-\text{CH}_2-\text{NH}-\text{CH}_2-\text{CH}_2-\text{OH}$
N-Isopropyl-1,3-propanediamine	$\text{H}_2\text{N}-\text{C}_3\text{H}_6-\text{NH}-\text{CH}(\text{CH}_3)_2$
	$\text{H}_2\text{N}-\text{C}_n\text{H}_{2n}-\text{NH}-\underset{\text{C}_p\text{H}_{2p+1}}{\overset{\text{C}_m\text{H}_{2m+1}}{\text{CH}}}$
Secondary-Secondary Diamines	
	$\text{H}_3\text{C}-\text{NH}-\text{C}_n\text{H}_{2n}-\text{NH}-\underset{\text{C}_p\text{H}_{2p+1}}{\overset{\text{C}_m\text{H}_{2m+1}}{\text{CH}}}$

C_nH_{2n} can be linear or branched such as $-(\text{CH}_2)_n-$ or $-\text{CH}_2-\text{CH}(\text{CH}_3)-$, or $-\text{CH}_2-\text{C}(\text{CH}_3)_2-$ and n , m , and p are integrals equal to or larger than 1, preferably up to 18.

5

The process for making the NAFPO's preferably is carried out in a continuous process employing an extruder such as a co-rotating intermeshing BERSTORFF® twin-screw extruder under conditions that control cross-linking. This can be done by assuring that the mole concentration of the diamine is kept at a mole amount at least equal to the

10

mole amount of the electrophilic group of the reactive resin throughout the process, preferably about 1.2 times (more preferably at least 2 times) the mole amount of the electrophilic group of the reactive resin. To assure that this condition exists throughout the reaction, special startup and shutdown procedures are preferred. On startup, for example, the extruder preferably is initially flushed with a non-reactive resin, for example high density polyethylene (HDPE) resin such as SCLAIR®2907 resin. With the non-reactive resin still being fed to the extruder, the diamine, for example 1,3-pentanediamine (DuPont trade-mark Dytek®EP), feed is then started. When the diamine feed is established, the resin feed is switched from the non-reactive resin to the reactive resin, for example EPDM resin grafted with 0.65 wt% maleic anhydride (MAH).

Preferably, sufficient inert gas such as nitrogen is co-currently injected into a middle barrel section of the extruder, dispersing and compressing the gas into the polymer melt, then allowing the gas to expand and generate a large amount of surface so that any residual diamine can be efficiently removed from the resulting NAFPO. Inert gas flow should be at a rate equal to at least 0.1 weight percent based on the reactive resin, preferably at least 2 weight percent, more preferably up to 5 weight percent. Higher inert gas flow rates are preferred for higher levels of diamine feed. Alternately to co-current up-stream enhanced devolatilization, down-stream counter-current devolatilization techniques can be used.

Flow of diamine, reactive resin and inert gas are maintained until desired product is made. Then the inert gas flow is discontinued and the reactive resin feed is switched to the non-reactive resin (HDPE, for example). The diamine injection is continued for sufficient time, say 5 more minutes, to assure that all reactive resin has been flushed from extruder before diamine feed is stopped. Flushing of the extruder with the non-reactive resin is continued after the diamine feed is stopped until no diamine is detected in the polymer exiting the extruder.

Electrophilic Functional Groups

The term "electrophilic functional groups" as used herein relates to chemical groups which can withdraw electrons from other chemical groups. The polymer carrying an electrophilic functional group in accordance with this invention may be the following:

- (i) Polyolefin grafted with Grafting Monomer;
- (ii) Copolymers of olefin and vinyl monomers.

Polyolefin Grafted with Grafting Monomer


The "grafted polyolefin" may be formed from at least one of a homopolymer of ethylene, a homopolymer of propylene, copolymers of ethylene and propylene especially copolymers of propylene with minor amounts of ethylene as in impact and random copolymer polypropylene, 5 terpolymers of ethylene, propylene and dienes, *e.g.* EPDM marketed by DuPont under the tradename NORDEL®, or a copolymer of ethylene with at least one of a C₃-C₁₈ alpha-olefins. Examples of the alpha-olefins include butene-1, hexene-1 and octene-1. The copolymers may include both linear 10 low density polyethylene and very low density polyethylene.

The grafting monomer is at least one monomer selected from ethylenically unsaturated carboxylic acids and ethylenically unsaturated carboxylic acid anhydrides, including, less preferably, derivatives of such acids, and mixtures thereof. Examples of the acids and anhydrides, which 15 may be mono-, di- or polycarboxylic acids, are acrylic acid, methacrylic acid, maleic acid, fumaric acid, itaconic acid, crotonic acid, itaconic anhydride, maleic anhydride, and substituted maleic anhydride, *e.g.* dimethyl maleic anhydride or citraconic anhydride, nadic anhydride, nadic methyl anhydride, and tetrahydrophthalic anhydride, maleic anhydride being particularly 20 preferred. Examples of the derivatives of the unsaturated acids are salts, amides, imides and esters, *e.g.* mono- and disodium maleate, acrylamide, maleimide, glycidyl methacrylate and dimethyl fumarate. Techniques for the grafting of such monomers onto the polyolefin are known, *e.g.* as described in U.S. Patent Number 4,612,155 of R.A. Zelonka and C.S. Wong, which issued 25 September 16, 1986, and in published European Patent Application Number 0,398,604 of D.J. Mitchell, published May 23, 1990. The present invention will be particularly described herein with reference to maleic anhydride as the grafting monomer.

In particular the example herein shall be described with 30 reference to maleic anhydride grafted polyolefin (PO-g-MAH) sold by DuPont Canada under the trademark FUSABOND® which includes maleic anhydride grafted polypropylene (PP-g-MAH).



Accordingly, the nucleophilic amine functionalized polyolefins (NAFPO's) in accordance with one embodiment of this invention are made 35 by melt processing of maleic anhydride modified or grafted polyolefins with the diamines as referred to above. In particular, the two amino groups of the diamines have different reactivity towards the anhydride on the polyolefins. In other words, the NAFPO's are produced by diamine derivatization of

anhydride functionalized polyolefins, and in one specific example by derivatization of FUSABOND® (trade-mark of DuPont Canada) with diamines. During melt processing, one amino group of the diamines is reacted with the anhydride and the other remains as the new functionality, namely a reactive nucleophilic amino group. For example, the following is illustrative of a typical reaction:



where PO is a polyolefin
 R₁ is a bivalent organic radical
 R₂ may be H or alkyl group.

More specific examples of the foregoing illustrating diamines that can be used in accordance with this invention include:



The nucleophilic amine functionalized polyolefins made by melt processing of maleic anhydride with the modified polyolefins known by DuPont Canada's trade-mark FUSABOND® with the diamines as referred to above have the following general chemical structure:

Polyolefin-imide linkage-R-Amine

where R is a divalent organic radical, and
 Amine is any nucleophilic secondary or primary amine

Copolymers of Olefin and Vinyl Monomer

Moreover, a further embodiment of this invention relates to the production of nucleophilic amine functionalized polyolefin by reacting a polymer carrying an electrophilic functional group with the diamine as referred to above, where the electrophilic functionalized polyolefin is produced by the copolymerization of one or more vinyl monomers with an electrophilic functional group and one or more of the following monomers, ethylene, propylene, C₄ - C₁₈ alpha-olefin, or diene monomer.

10

Polymers with Carboxylic Acid, Chlorinated Polyolefins, Epoxy, Sulphonic Acid, and Anhydride

Another embodiment of the invention relates to the method of producing nucleophilic amine functionalized polyolefins by utilizing a polymer carrying an electrophilic functional group where the electrophilic functional group is selected from the group carboxylic acid (COOH), chlorocarbon (C-Cl), epoxy, sulphonic acid (-SO₃H), and anhydride. The following illustrates a typical reaction, namely:

20




where Y is an electrophilic functional group such as COOH, C-Cl, epoxy, -SO₃H, anhydride;
X, R₁ and R₂ are defined above.

25

Composition

This invention also relates to a nucleophilic amine functionalized polyolefin composition having the structure:

30



where X is selected from the group of imide, amide, sulphonamide or amine
R₁ is a bivalent organic radical
R₂ is H or an alkyl group

35

The symbol X will have the structure referred to below, when producing the nucleophilic amine functionalized polyolefins in accordance

with the process referred to above when utilizing the electrophilic functional group as follows:

\times	<u>Electrophilic Functional Group</u>
imide	anhydride
amide	carboxylic acid
amine	epoxy
sulphonamide	sulphonic acid
amine	chlorinated polyolefins

In other words by melt processing the maleic anhydride modified polyolefins identified by DuPont Canada's trade-mark FUSABOND[®] with the diamines, the following nucleophilic amine functionalized polyolefin composition is produced, namely:

Polyolefin - imide - R₁ - NHR₂

10

where R₁ is a bivalent organic radical
R₂ is H or an alkyl group


Compatibilizers

15

NAFPO's can be used as compatibilizers to make blends or alloys of polyolefins which are otherwise incompatible.

For example, the compatibility of generally immiscible polyolefin A (PO_A) and polyolefin B (PO_B) may be improved by utilizing a NAFPO.

The following is illustrative of such reaction, namely:



Examples

5 Such reaction may be further particularized by the following example which shall serve as being illustrative of one example utilizing NAFPO's as compatibilizers:

Example of Compatibilizer

10 Generally speaking, polypropylene and polyethylene are immiscible polyolefins. In this example, we select polyolefin PO_A as polyethylene, and polyolefin PO_B as polypropylene.

15 In this example a blend of approximately 30% by weight of polypropylene to 70% by weight of polyethylene is produced. Such blend may be produced by utilizing 63.6% by weight of polyethylene and 3.9% of polyethylene which has been grafted with maleic anhydride, namely PE-g-MAH. 27.3% by weight of polypropylene may also be utilized along with 5.2% by weight of nucleophilic amine functionalized polypropylene (NAFPO P) made in accordance with the invention herein.

20 Although this example shows the use of 3.9% by weight of PE-g-MAH, and 5.2% by weight of NAFPO P, the compatibilization of the polypropylene and polyethylene may be accomplished by utilizing a minimum of 0.1% to a maximum of 100% by weight of PE-g-MAH to polyethylene along with a minimum of 0.1% to a maximum of 100% NAFPO P to polypropylene. The ratio of PE-g-MAH to polyethylene and ratio of NAFPO P to polypropylene can be selected based on the economics of the process. In
25 other words, higher concentrations of PE-g-MAH and NAFPO P may be more costly.

In addition, the combination of PP-g-MAH and nucleophilic amine functionalized polyethylene (NAFPO E) can also bring about improved mechanical properties for PP/PE blends.

Moreover, in the example referred to herein the relative ratio
5 of polypropylene to polyethylene is approximately 30% to 70% by weight although the blend ratio can vary between 0.2% - 99.8% by weight of polypropylene to polyethylene.

Another example of utilizing NAFPO's as compatibilizers relates to blending polypropylene to ethylene propylene and diene modified
10 polymers, namely EPDM. In this example, a blend of approximately 70% by weight of polypropylene is blended with approximately 30% by weight of EPDM whereby 65% by weight of polypropylene is blended with 5% by weight of nucleophilic amine functionalized polypropylene made in accordance with the invention herein NAFPO P, with 5% by weight of
15 EPDM-g-MAH and 25% by weight of EPDM.

Examples 1-3:

The following examples for making the NAFPO were carried out in a 25 mm co-rotating intermeshing BERSTORFF® twin-screw extruder operating at screw speed of 250 revolutions per minute under conditions that
20 control cross-linking. The mole concentration of the diamine was kept higher than that of the anhydride throughout the process. The extruder was initially flushed with a non-reactive resin, for example high density polyethylene (HDPE) resin such as SCLAIR® 2907 resin. With the HDPE still being fed to the extruder, the diamine, for example 1,3-pentanediamine (DuPont trade-
25 mark Dytex® EP), feed was then started. When the diamine feed was established, the resin feed was switched from the HDPE to the reactive resin, for example EPDM resin grafted with 0.65 wt% MAH. Sufficient nitrogen was co-currently injected into a middle barrel section of the extruder, dispersed and compressed in the polymer melt, then allowed to expand and
30 generate a large amount of surface so that any residual diamine can be efficiently removed from the resulting NAFPO.

Flow of diamine, reactive resin and inert gas were maintained at appropriate levels until desired product was made. Then the nitrogen flow was discontinued and the reactive resin feed was switched to the non-reactive
35 resin (HDPE, for example). The diamine injection was continued, for say 5 more minutes, to assure that all reactive resin was flushed from extruder before diamine feed was stopped. Flushing of the extruder with the non-

reactive resin was continued after the diamine feed was stopped until no diamine was detected in the polymer exiting the extruder.

Example 1: Making EPDM based NAFPO

11.9 pounds/hour EPDM resin containing 0.65 wt% MAH was
5 reacted with 0.20 pounds/hour 1,3-pentanediamine (DuPont trade-mark
Dytek® EP) in a twin-screw extruder at 170° C. Nitrogen flow was about 1.6 -
1.7 standard liters per minute (SLPM), measured under standard conditions
of 25° C and 1 atmosphere. The starting EPDM resin has a Melt Flow Index
(MFI) of 10 g/10min (ASTM D1238, conditions E). The finished product has
10 MFI of 4.5 g/10 min under the same conditions. Infrared spectrum shows
complete conversion of anhydride group to imide functionality.

Example 2: Making PP based NAFPO

21.3 pounds/hour polypropylene resin containing 0.66 wt%
MAH was reacted with 0.28 pounds/hour N-(2-aminoethyl) piperazine (AEP)
15 in a twin-screw extruder at 200° C. Nitrogen flow was 1.6 - 1.7 SLPM. The
starting PP resin has a Melt Flow Index (MFI) of 105 g/10min (ASTM
D1238, conditions E). The finished product has MFI of 33.5 g/10 min under
the same conditions. Infrared spectrum shows complete conversion of
anhydride group to imide functionality.

Example 3: Making PE based NAFPO

13.5 pounds/hour polyethylene resin containing 0.8 wt% MAH
was reacted with 0.26 pounds/hour N-(2-aminoethyl)piperazine (AEP) in a
twin-screw extruder at 250° C. Nitrogen flow was 1.6 - 1.7 SLPM. The starting
PE resin has a Melt Flow Index (MFI) of 1.5 g/10min (ASTM D1238,
25 conditions E). The finished product has MFI of 0.2 g/10 min under the same
conditions. Infrared spectrum shows complete conversion of anhydride group
to imide functionality.

End Use Examples

Alloying PE/PP blend

30 A PE/PP 70/30 by weight blend was prepared on a twin-screw
extruder by mixing 63.6 parts PE, 27.3 parts PP, 3.9 parts PE containing 1
wt% MAH graft, and 5.2 parts PP based NAFPO prepared in Example 2.
This PE/PP alloy has Notched Izod impact strength of 0.81 ft. lb./in
compared with 0.36 ft. lb./in for a PE/PP 70/30 by weight blend without
35 NAFPO.

NAFPO in Nylon Blends

The nucleophilic amino functionality of NAFPO can react with
carboxylic acid group in Nylon. This allows the use of NAFPO in the

preparation of Nylon blends. Such compatibilized Nylon/Polyolefin blends have superior mechanic properties than the non-compatibilized blends. For example, Nylon/EPDM blends with less than 20 wt% NAFPO have much higher impact resistance and stiffness than the same blends without NAFPO.

- 5 Traditionally, Nylon/Polyolefin blends have been compatibilized using the amino group from Nylon and the anhydride or carboxylic acid group from polyolefins. However, the recycled Nylon stream such as in Nylon carpet yarn contains no amino group but predominantly consists of carboxylic acid group. The carboxylic acid group can be also introduced to Nylon during the Nylon
10 synthesis by end group controlling technology largely available in commercial Nylon production processes. Therefore NAFPO can be used for compounding of both virgin and recycled Nylon products.

NAFPO can be used for blending nylon with polyolefins such as PE, PP, ethylene-propylene rubber, or EPDM.

15 **Adhesives**

The NAFPO's produced in accordance with this invention may also be utilized as effective adhesives with various substrates such as nylon, PVC, and MYLAR® film.

Other Uses

- 20 Moreover, the NAFPO's described herein may be utilized as dye sites for acidic dyes, as well as immobilized nucleophiles to extract hazardous acids and immobilized acid traps or scavengers. Examples of acid trap reactions and immobilized nucleophiles include:





25





Carboxylic Acid, Chlorination Polyolefins, Epoxy, Sulphonic acid, Anhydride

- 30 Further examples of applications of NAFPO's to compatibilize PO_B and PO_A by utilizing polymers carrying an electrophilic functional group selected from the group of carboxylic acid, chlorinated polyolefins, epoxys, sulphonic acids, and anhydrides includes the following:



5



10

Although the preferred embodiment as well as the operation and the use have been specifically described in relation to the drawings, it should be understood the variations in the preferred embodiment could be achieved by a man skilled in the art without departing from the spirit of the

15 invention.


CLAIMS

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

- 5 1. A method of producing nucleophilic amine functionalized polyolefin by reacting a polymer carrying an electrophilic functional group with at least one mole of a diamine or its salt per mole of the electrophilic functional group, wherein the diamine or salt has amino end-groups having different reactivities.
- 10 2. The method as claimed in claim 1 wherein said diamine has the structure:
 $H_2N - R_1 - NHR_2$
- wherein R_1 is a bivalent organic radical, and
15 R_2 is a H or alkyl group.
3. The method as claimed in claim 2 wherein said electrophilic functional group is selected from the group consisting of COOH, C-Cl, epoxy, -SO₃H and anhydride.
4. The method as claimed in claim 3 wherein said
20 electrophilic functional group is COOH.
5. The method as claimed in claim 3 wherein said electrophilic functional group is anhydride.
6. The method as claimed in claim 2 wherein said polymer carrying said electrophilic functional group is produced by:
25 copolymerization of one or more vinyl monomers with an electrophilic functional group, and one or more of the following monomers: ethylene, propylene, C₄ - C₁₈ alpha-olefin, or diene monomers.
7. The method as claimed in claim 2 wherein said polymer carrying said electrophilic functional group comprises:
30 grafted polymer being selected from at least one of homopolymers of ethylene and propylene, copolymers of ethylene and propylene, terpolymers of ethylene, propylene and diene and copolymers of ethylene, propylene, C₄-C₁₈ alpha-olefin, or diene monomers that has been grafted with at least one monomer selected from ethylenically unsaturated
35 dicarboxylic acids and anhydrides thereof, and derivatives thereof;
8. The method as claimed in claim 7 wherein said grafting monomer is maleic anhydride.

9. The method as claimed in claim 8 wherein said grafted polymer is selected from the group polyethylene, polypropylene, EPDM and ethylene-propylene rubber.

10. A nucleophilic amine functionalized polyolefin
5 composition having the structure:



where X is selected from the group of imide, amide, sulphonamide or
amine,

10 R₁ is a bivalent organic radical, and

R₂ is H or an alkyl group.

11. A multi-phase thermoplastic composition blend consisting essentially of 0.2 - 99.8% by weight of Polyolefin A and 99.8% - 0.2% by weight of Polyolefin B where:

15 (a) said Polyolefin A and Polyolefin B are immiscible polymers selected from the group of homopolymer of ethylene, homopolymer of propylene, copolymer of ethylene and propylene, terpolymers of ethylene, propylene and diene, and copolymers of ethylene, propylene, C₄ - C₁₈ alpha-olefin, or diene monomers;

20 (b) Polyolefin A carrying an electrophilic functional group where the total amount of electrophilic functionalized Polyolefin A to Polyolefin A is between 0.1% to 100% by weight;

25 (c) Polyolefin B carrying a nucleophilic amine functional group where the total amount of nucleophilic amine functionalized Polyolefin B to Polyolefin B is between 0.1% to 100% by weight.

12. The composition blend as claimed in claim 11 where said Polyolefin A carrying said electrophilic functional group comprises:

30 (a) copolymers of one or more vinyl monomers with an electrophilic functional group, and one or more of the following monomers: ethylene, propylene, C₄ - C₁₈ alpha-olefin, or diene monomers; and/or

35 (b) grafted polymer being selected from at least one of homopolymers of ethylene and propylene, copolymers of ethylene and propylene, terpolymers of ethylene, propylene and diene and copolymers of ethylene, propylene, C₄-C₁₈ alpha-olefin, or diene monomer that has been grafted with at least one monomer selected from ethylenically unsaturated dicarboxylic acids and anhydrides thereof, and derivatives thereof;

and said nucleophilic amine functionalized Polyolefin B has the structure:

- Polyolefin B - X - R₁ - NHR₂
- where X is selected from the group of imide, amide, sulphonamide or amine,
- R₁ is a bivalent organic radical, and
- 5 R₂ is H or an alkyl group.
13. The composition as claimed in claim 11 wherein Polyolefin A is polypropylene and Polyolefin B is polyethylene and said grafting monomer is maleic anhydride.
14. A process for improving the blending of Polyolefin A and Polyolefin B where said Polyolefin A and Polyolefin B are immiscible polymers selected from the group of homopolymers of ethylene, homopolymers of propylene, terpolymers of ethylene, propylene and diene, copolymers of ethylene, propylene, C₄ - C₁₈ alpha-olefin, or diene monomer by adding:
- 15 (a) Polyolefin A carrying an electrophilic functional group where the total amount of electrophilic functionalized Polyolefin A to Polyolefin A is between 0.1% to 100% by weight;
- (b) Polyolefin B carrying a nucleophilic amine functionalized Polyolefin B where the total amount of nucleophilic amine functionalized
- 20 Polyolefin B to Polyolefin B is between 0.1% to 100% by weight.
15. The process as claimed in claim 14 wherein:
- (a) said Polyolefin A is polyethylene;
- (b) said Polyolefin A carrying an electrophilic functional group is polyethylene grafted with maleic anhydride;
- 25 (c) said Polyolefin B is polypropylene;
- (d) where said nucleophilic amine functionalized Polyolefin B is
- Polypropylene-X - R₁ - NHR₂
- where X is selected from the group of imide, amide, sulphonamide or amine,
- 30 R₁ is a bivalent organic radical, and
- R₂ is H or an alkyl group.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/CA 96/00141

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F8/32 C08L23/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 440 922 (SUMITOMO CHEMICAL COMPANY, LTD.) 14 August 1991 see the whole document ---	1-3, 10-15
A	EP,A,0 422 804 (DU PONT DE NEMOURS AND COMPANY) 17 April 1991 see claims 1-15 ---	1
A	DE,C,36 29 167 (TH. GOLDSCHMIDT AG) 16 April 1987 see the whole document ---	1
A	FR,A,1 446 341 (HOECHST AG) 13 June 1966 see the whole document ---	1
A	US,A,3 219 639 (W. M. FUCHS) 23 November 1965 see claims 1-7 -----	1

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

12 June 1996

Date of mailing of the international search report

20. 06. 96

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Permentier, W

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/CA 96/00141

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-440922	14-08-91	CA-A- 2031868	12-06-91
		DE-D- 69026066	25-04-96
		JP-A- 3227369	08-10-91
		US-A- 5218048	08-06-93

EP-A-422804	17-04-91	CA-A- 2026460	30-03-91
		JP-A- 3188107	16-08-91

DE-C-3629167	28-11-91	CA-A- 1306150	11-08-92
		CA-A- 1319223	15-06-93
		EP-A,B 0259652	16-03-88
		IE-B- 59715	23-03-94
		JP-B- 6043262	08-06-94
		JP-A- 63064943	23-03-88
		US-A- 4792494	20-12-88
US-A- 4908237	13-03-90		

FR-A-1446341	10-10-66	BE-A- 663044	26-10-65
		DE-A- 1495796	13-11-69
		GB-A- 1109671	
		US-A- 3417061	17-12-68

US-A-3219639	23-11-65	NONE	
